



Mortar Sand

Code: [39-1170](#)

Product Group: [Moulding of Prisms](#)

Graded pack for 3 prisms. 1350g pack.

Complies to EN 196-1, EN 196-9, BS 1881, ASTM C778 & ISO 679

Physical state: solid

SiO₂: > 95 %

Form: crystallized

Form of grains: subangular - Color: white - Smell :
odourless - pH: # 7

Specific temperature for changes in physical state:

Fusion temperature: 1610° C, boiling temperature:
2230°C

Decomposition temperature: none

Flash Point: not applicable

Mass volume: absolute: 2,63 g/m³ - apparent: 1,6
g/cm³

Solubility: insoluble in water, soluble in hydro-fluoric
acid


Standards

EN 196-1, EN 413-2, EN 459-2, EN 1744-1, EN 1015-10, EN 1015-11, EN 13454-2, ISO 679, BS 3892-1, BS 4551-1

Further Information

NOT AVAILABLE FOR SALE IN THE USA

Accessories



Three-gang Mould

Code: [39-1100](#)